

KT-820 CF30

KetaSpire KT-820 CF30 is the low-flow, 30% carbon-fiber reinforced grade of polyetheretherketone (PEEK). Carbon-fiber reinforcement of KetaSpire PEEK provides the maximum levels of mechanical properties at temperatures approaching 300°C, and the lowest coefficient of linear thermal expansion within the KetaSpire product family.

KetaSpire PEEK is produced to the highest industry standards and is characterized by a distinct combination of properties, which include excellent wear resistance,

best-in-class fatigue resistance, ease of melt processing, high purity, and excellent chemical resistance to organics, acids, and bases.

These properties make it well-suited for applications in healthcare, transportation, electronics, chemical processing, and other industrial uses. KetaSpire KT-820 CF30 can be easily processed using typical injection molding and extrusion processes.

Typical Properties of KetaSpire KT-820 CF30 Resin

Property	ASTM Test Method	Typical Values ⁽¹⁾			
		U.S. Customary Units		SI Units	
		Value	Units	Value	Units
Mechanical					
Tensile Strength	D 638	29.1	kpsi	201	MPa
Tensile Modulus	D 638	2,860	kpsi	19.7	GPa
Tensile Elongation at Break	D 638	2.0	%	2.0	%
Flexural Strength	D 790	46.0	kpsi	317	MPa
Flexural Modulus	D 790	2,540	kpsi	17.5	GPa
Izod Impact, Notched	D 256	1.3	ft-lb/in	69	J/m
Izod Impact, Unnotched	D 4812	14	ft-lb/in	750	J/m
Thermal					
Deflection Temperature at 264 psi (1.82 MPa)	D 648	599	°F	315	°C
Glass Transition Temperature	D 3418	302	°F	150	°C
Melting Point	D 3418	644	°F	340	°C
Coefficient Linear Thermal Expansion ⁽²⁾	E 831	2.9	ppm/°F	5.2	ppm/°C
General and Fabrication					
Specific Gravity	D 792	1.41		1.41	
Water Absorption, 24 hours	D 570	0.1	%	0.1	%
Melt Flow, 400°C, 2.16 kg	D 1238	1.1	g/10 min	1.1	g/10 min
Mold Shrinkage, flow direction	D 955	0.1	%	0.1	%
Mold Shrinkage, transverse direction	D 955	0.5	%	0.5	%

⁽¹⁾ Properties shown are typical of limited production and final specification ranges may vary. Values are typical of uncolored resin, addition of colorants or other additives may alter properties.

⁽²⁾ Measured in flow direction over the temperature range -50°C to 50°C

Drying

KetaSpire resins must be dried completely prior to melt processing. Incomplete drying will result in defects in the formed part ranging from surface streaks to severe bubbling. Pellets can be dried on trays in a circulating air oven or in desiccating hopper dryer. Drying conditions recommended are 4 hours at 150°C (300°F) .

Injection Molding

KetaSpire resins can be readily injection molded in most screw injection machines. A general purpose screw with a compression ratio in the range of 2.5 to 3.5 to 1 is recommended, as is minimum back pressure. Injection speeds should be as fast as possible, consistent with part appearance requirements. Mold temperatures in the range of 350°F to 400°F (177°C to 204°C) are suggested. Recommended starting point barrel temperature settings are shown in the following table.

Zone heater settings		
Zone	Recommended Barrel Temperatures	
	°F	°C
Rear (Feed)	690	365
Middle	700	371
Front	710	377
Nozzle	720	382

Standard Packaging and Labeling

KetaSpire resins are packaged in polyethylene buckets or cardboard boxes depending upon the order size.

Individual packages will be plainly marked with the product number, the color, the lot number, and the net weight.

Product Safety and Emergency Service

For product safety information or a Material Safety Data Sheet on a product of Solvay Advanced Polymers

1 (800) 621-4557

1 (770) 772-8880 outside of U.S.

For information or help in an emergency such as a spill, leak, fire or explosion, call day or night:

Emergency Health Information

1 (800) 621-4590

1 (770) 772-5177 outside of U.S.

Emergency Spill Information

CHEMTREC 1 (800) 424-9300

1 (703) 527-3887 outside of U.S.

collect calls accepted

For Additional Information

Technical Service

1 (800) 621-4557

Customer Service

1 (800) 848-9744

KetaSpire is a registered trademark of Solvay Advanced Polymers, L.L.C.

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Advanced Polymers, LLC nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Solvay Advanced Polymers, LLC reserves the right to make additions, deletions, or modifications to the information at any time without prior notification.