

# Torlon® 5030

## polyamide-imide

Torlon® 5030 is a 30% glass-fiber reinforced grade of polyamide-imide (PAI) resin. It offers high strength and modulus and exceptional creep resistance. It has thermal expansion characteristics similar to aluminum and therefore excellent dimensional stability.

Torlon® PAI has the highest strength and stiffness of any thermoplastic up to 275°C (525°F). It has outstanding resistance to wear, creep and chemicals.

The mechanical properties of Torlon® 5030 resin make it a candidate for metal replacement in high temperature, high stress applications. In addition, it offers outstanding electrical properties, which makes it ideal for high performance parts such as connectors, switches and relays.

- High Flow: Torlon® 5030-HF
- Low Flow: Torlon® 5030-LF
- Extrusion Grade: Torlon® 5030-E

### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Flame Retardant • Good Chemical Resistance • Good Compressive Strength	• Good Creep Resistance • Good Dimensional Stability • High Heat Resistance	• High Stiffness • High Temperature Strength
Uses	• Aerospace Applications • Aircraft Applications • Automotive Applications • Business Equipment • Connectors • Electrical Housing	• Electrical Parts • Electrical/Electronic Applications • Housings • Industrial Applications • Industrial Parts • Machine/Mechanical Parts	• Metal Replacement • Oil/Gas Applications • Sealing Devices • Switches • Valves/Valve Parts
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Injection Molding	• Machining	• Profile Extrusion

Physical	Typical Value	Unit	Test method
Specific Gravity	1.61		ASTM D792
Molding Shrinkage - Flow	0.10 to 0.25	%	ASTM D955
Water Absorption (24 hr)	0.24	%	ASTM D570


Mechanical	Typical Value	Unit	Test method
Tensile Modulus	14500	MPa	ASTM D638
Tensile Strength	221	MPa	ASTM D638
Tensile Stress	205	MPa	ASTM D1708
Tensile Elongation			
Break	2.3	%	ASTM D638
Break <sup>1</sup>	7.0	%	ASTM D1708
Flexural Modulus			ASTM D790
23°C	11700	MPa	
232°C	9860	MPa	

# Torlon® 5030


polyamide-imide

<b>Mechanical</b>	<b>Typical Value</b>	<b>Unit</b>	<b>Test method</b>
Flexural Strength			ASTM D790
23°C	333	MPa	
232°C	181	MPa	
Compressive Modulus	7930	MPa	ASTM D695
Compressive Strength	264	MPa	ASTM D695
<b>Impact</b>	<b>Typical Value</b>	<b>Unit</b>	<b>Test method</b>
Notched Izod Impact	80	J/m	ASTM D256
Unnotched Izod Impact	530	J/m	ASTM D4812
<b>Thermal</b>	<b>Typical Value</b>	<b>Unit</b>	<b>Test method</b>
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	282	°C	
Thermal Conductivity	0.36	W/m/K	ASTM C177
Coefficient of Linear Thermal Expansion	1.6E-5	cm/cm/°C	ASTM D696
<b>Electrical</b>	<b>Typical Value</b>	<b>Unit</b>	<b>Test method</b>
Surface Resistivity	1.0E+18	ohm	ASTM D257
Volume Resistivity	2.0E+17	ohm·cm	ASTM D257
Dielectric Strength	33	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	4.40		
1 MHz	4.20		
Dissipation Factor			ASTM D150
60 Hz	0.022		
1 MHz	0.050		
<b>Injection</b>	<b>Typical Value</b>	<b>Unit</b>	
Drying Temperature	177	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	304	°C	
Nozzle Temperature	371	°C	
Mold Temperature	199 to 216	°C	
Back Pressure	6.89	MPa	
Screw Speed	50 to 100	rpm	
Screw L/D Ratio	18.0:1.0 to 24.0:1.0		

Isothermal Stress vs. Strain (ISO 11403-1)



Viscosity vs. Shear Rate (ISO 11403-2)



**Notes**

Typical properties: these are not to be construed as specifications.

<sup>1</sup> ASTM Test Method D1708 has been used to measure the tensile properties of PAI and similar materials because the small test specimen conserved material.

Today the most widely used specimen is the Type 1 bar of ASTM D638. These D1708 values are included for historical purposes and they should not be compared to the D638 values.

---

**[www.solvay.com](http://www.solvay.com)**

**[SpecialtyPolymers.EMEA@solvay.com](mailto:SpecialtyPolymers.EMEA@solvay.com)** | Europe, Middle East and Africa

**[SpecialtyPolymers.Americas@solvay.com](mailto:SpecialtyPolymers.Americas@solvay.com)** | Americas

**[SpecialtyPolymers.Asia@solvay.com](mailto:SpecialtyPolymers.Asia@solvay.com)** | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2014 Solvay Specialty Polymers. All rights reserved.